High performance defoamer

RP-6419

Features and advantages:

RP-6419 is used as a defoamer for solvent-based, solvent-free and radiation-curable coatings, especially for radiation-curable systems and two-component epoxy systems and color paint formulations. Good foam suppression effect, construction spraying foaming ability is strong, also suitable for thick coating. Application: amine/amide cured epoxy floor coatings, solvent-based and radiation cured screen printing inks, radiation cured varnish, wood and furniture coatings, amine/amide cured epoxy baking paint.

○ For solvent-based, solvent-free and radiation curing formulations

○ Especially suitable for color paint formula

○ High efficiency

○ Solvent-free

Product specification：

Appearance	liquid
Solid content	100%
Composition	Organic modified polysiloxane, containing fumed silica

Application field:

○ Amine/amide cured epoxy floor coating

Recommended addition

Total formula in the form of supply: 0.1-1.0%

○ Solvent-based and radiation-cured screen printing inks

Recommended addition

Total formula in the form of supply: 0.1-1.0

○ Radiation curing varnish

Recommended addition

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; For more information, please visit: https://www.rk-chem.com

Total formula in the form of supply: 0.1-1.0%

○ Wood and furniture coatings

Recommended addition

Total formula in the form of supply: 0.1-0.8%

○ Amine/amide cured epoxy paint

Recommended addition

Total formula in the form of supply: 0.1-1.0%

○ Leather Paint

Recommended addition

Total formula in the form of supply: 0.1-0.8%

Usage:

○ When used for color paint formulation, it is recommended to add in the grinding stage

○ Stir before use

○ Pre-dilution with the recommended solvent will facilitate addition and mixing

○ Pre-dilution or directly added to the paint according to the supply form can be

○ Must be mixed with high shear force

Packing:

25kg plastic drum / 200kg iron drum

Storage:

Store unopened original packaging without freezing and use within 12 months.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; For more information, please visit: https://www.rk-chem.com